



8280 14<sup>th</sup> Avenue, Sacramento, CA 95826  
1-916-454-2560 Fax 1-916-452-1836

## OverKote<sup>®</sup> Crack Filler II

Manufactured By Reed & Graham in San Jose, CA

### DESCRIPTION:

An emulsified petroleum asphalt and suitable fillers, modified with latex rubber. This cold-applied product is designed for use in filling cracks in asphaltic concrete pavements.

### MATERIAL SPECIFICATIONS:

#### SPECIFICATIONS

Weight/Gallon  
Residue, %  
Flexibility  
Solubility of residue in C<sub>2</sub>HCl<sub>3</sub> %  
Firm Set  
Ash content of insoluble Residue, %  
Viscosity @ 77°, Brookfield Spindle #6, 1 RPM  
7 Day Viscosity  
Water resistance

#### LIMITS

1.210 Min G/CM<sub>3</sub>  
75-85  
Pass  
89-95  
90 minutes  
70 minutes  
140-170 poise  
140-170 poise  
Pass

#### METHOD

Gardener Cup  
ASTM D 2939  
ASTM D 2939 \*\* (b)  
ASTM 2042  
ASTM D 2939 \*\* (a)  
ASTM D 2939  
Brookfield Method  
Brookfield Method  
ASTMD 2939, Alternative B

\*\*Modifications

(a) Test @ 30 minute intervals - Cast on 15# felt.

(b) Air Dry to constant Weight @ 75 ± relative humidity; condition mandrel and specimens 2 hours @ 60°F before test.

### PREPARATION:

Cracks should be clean and preferably moist or damp. If necessary, dirt, loose pieces of old expansion joint material, or other obstructions in the joints or cracks shall be removed with an air jet or water or both. The surface of the pavement should be air-dry when the application of crack filler is made.

### APPLICATION:

Mix well before using. Use as received, without dilution or addition of materials which might change its consistency. Pour Crack Filler into cracks. Cracks should be filled approximately to the surface of the pavement. Product can be applied by means of cone-shaped crack filler devices, pouring pots, "V" shaped squeegees and/or other appropriate equipment that will induce the Crack Filler into the joint without undue waste. For best results, use a "V" shaped squeegee to insure that the appropriate quantity of Crack Filler is used without leaving excessive product on the pavement surface. Allow Crack Filler to cure before proceeding with pavement sealing.

### COVERAGE:

Indefinite.

### PRECAUTIONS:

Do not use in cracks exceeding 1/2" in width. Air Temperature shall be at least 55°F and rising. Do not apply if rain is forecast within 48 hours after application. Wash tools in water. Use paint thinner if material has dried. Keep from freezing. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of reach of children.

### PACKAGING:

1 gallon jugs, 5 gallon pails, 50 gallon drums, Bulk.

Due to the wide range of variables affecting the results of application, such as weather conditions, construction equipment, and quality of other materials, there is no warranty, expressed or implied, that following this specification, or using the materials covered thereby, will assure satisfactory results.