



8280 14th Avenue, Sacramento, CA 95826



OverKote[®] Plus

DESCRIPTION:

Modifier for asphalt emulsion sealer.

GENERAL:

Overkote[®] Plus is a specially blended copolymer emulsion along with effective resistance additives to modify asphalt emulsion sealer to achieve outstanding toughness, color enhancement, fast curing time, greater flexibility, high viscosity, good suspension of the aggregates. It is recommended on any asphalt surface where there are high traffic patterns. Excellent for commercial and industrial parking lots, airport runways, traffic safety islands and service stations.

SURFACE PREPARATION:

Surface must be clean, free from dirt, dust and oil. Treat oil, grease and gasoline with Overkote[®] Oil-Spot Seal.

APPLICATION:

Mix well before using. Use Overkote[®] Plus 1 to 5 gallons to modify 100 gallons of asphalt emulsion sealer, undiluted. The amount will vary and depend upon the type of end use in the traffic pattern areas or specifications.

Always pour sealer first into mechanical spray or squeegee type machine then add proper amount of water. When agitating, add Overkote[®] Plus slowly and mix to uniform consistency. Then add proper amount of aggregates (silica sand, or any other specified aggregates) and mix thoroughly before application.

COVERAGE:

Depends on specification.

CAUTIONS:

Wash tools in water. Use a suitable paint thinner if material has dried. Keep from freezing. Do not store in direct sunlight. Container should be closed when not in use. Keep out of the reach of children.

PACKAGING:

5 gallon pails, 50 gallon drums.

TYPICAL PROPERTIES

• Appearance	White Liquid
• Nonvolatile Content %	55.0 ± 1.0
• pH	4.5 - 5.5
• Viscosity, Brookfield, RVF, 25°C #3 @ 60 rpm, cps	500-1,500
• Density, g/ml	1.06-1.10
• U.S. lb./gal.	8.85-9.15
• Glass Transition Temperature, °C	+20

Due to the wide range of variables affecting the results of application, such as weather conditions, construction equipment and quality of other materials, there is no warranty, expressed or implied, that following this specification, or using the materials covered thereby, will assure satisfactory results.

MATERIAL SAFETY DATA SHEETS AVAILABLE ON REQUEST