



8280 14<sup>th</sup> Ave, Sacramento, CA 95826

**Product Specifications**

**Product:** Emulsified Asphalt

**Grade:** SS-1h

**Description:** A highly stabilized anionic mixing type emulsion manufactured from hard base asphalt, suitable for use in soil stabilization, seal coating, and dust palliation.

	ASSTHO	Test Results	Specification
Viscosity, 25° C, SFS	T59	40	20-100
Sieve, w%	T59	0.01	0.10 Max
Storage Stability, 1 Day, %	T59	NA	1.0 Max
Settlement, 5 Days, %	T59	1%	5.0 Max
Cement Mixing, w %	T59	<2%	2.0 Max
Residue by Distillation, w %	T59	62	57.0 Min
Test on Residue			
Penetration, 25° C, dmm	T49	50	40-90
Ductility, 25° C, cm	T51	75	40 Min.
Solubility in Trichloroethylene, %	T44	99.9	97.5 Min.

Material meets Caltrans requirements M140

DOT Shipping Name: Asphalt, Non-hazardous

DOT Placard: None required

Released: 07-01-2019